

ANTICORRay Epoxy Primer 801

CORROSION PROTECTION

PRODUCT DESCRIPTION

Component A – epoxy base in an aluminium can for mixing with the entire volume of component B.

Component B – hardener (polyamide resin) in aluminium foil in quantity sufficient for component A.

TECHNICAL DATA

| Parameter | Component A | Component B |
|---|--------------------------|--------------------------|
| Density | ≈ 1,59 g/cm ³ | ≈ 0,96 g/cm ³ |
| Mixing ratio by weight | 100 | 30 |
| Boiling point | 280°C | - |
| Required class (in accordance to PN ISO-8501) | Sa 2 ^{1/2} | Sa 2 ^{1/2} |
| Colour | Black | Honey |
| Single packaging (kit) | Alu can 100 g | Alu foil 30 g |
| Multipack | 20 l | 20 l |

Product holds the certificate of the DVGW Institute and building mark „B”.

Product is the element of corrosion protection system ANTICORRay WSS60 and ANTICORRay WSS80.



ANTICOR Sp. z o.o. holds the ISO 9001 certificate.

ANTICORRay Epoxy Primer 801

The liquid non-solvent corrosion coating made of two components: epoxy base & hardener.

APPLICATION

- The first main layer of corrosion coating for steel pipelines.

FEATURES & ADVANTAGES

- Legally protected, highly specialised and unique formula of the epoxy primer. Ensures higher coating tightness at connection points with factory-made insulation.
- Very strong adherence to cleaned and prepared steel surface.
- High resistance to shear forces.
- The material is supplied in handy kits with necessary mixing and application accessories.

USAGE

- Apply onto steel surface that has been cleaned in grade Sa 2^{1/2} (ISO 8501), and heated to 70-80°C (according to the application method of ANTICORRay WSS60).

STORAGE

- Store the product in dry area in original packaging.
- Protect the cartons against mechanical damage.
- The recommended storage temperature: up to 25°C.

PRODUCT FORM & SIZE AVAILABLE

Can: Component A vol. 100 g.

Foil: składnik B vol. 30 g.

Other sizes available on individual request.