

# ANTICORRay Primer 720HT

## CORROSION PROTECTION

### STRUCTURE

**Solids:**

Butyl rubber and hydrocarbon resin

**Solvent:**

Petroleum spirit.

**Colour:** black.

### TECHNICAL DATA

Parameters	Unit	Value
Drying time	min	5-15
Density (in 20°C)	kg/dm <sup>3</sup>	0.78
Flash point	°C	-12
Coverage rate	l/m <sup>2</sup>	0.2



ANTICOR Sp. z o.o. holds the ISO 9001:2015 certificate.

### ANTICORRay Primer 720HT

Corrosion protection primer for steel surface protection systems, according to EN 12068, DIN 30672 and ISO 21809-3 for continuous operating temperature up to +80°C. Optional for use of heat shrinkable sleeve ANTI-CORRAY MSS50.

### RECOMMENDED USE / DESIGNED FOR

- Basic layer of corrosion protection in multi-layer sleeve systems, applied to the cleaned steel surface.
- Temporary corrosion protection of pipelines, steel tanks and fittings.

### FEATURES AND ADVANTAGES

- Effective protects steel surfaces against the effects of factors initiating corrosion processes.
- Contains Stress Corrosion Cracking inhibitors (SCC).
- Possess very good penetrating properties.
- Increases adhesion of coating to the protected steel surfaces.

### APPLICATION

- Before applying the primer, condition the primer at the temperature above 15°C and mix thoroughly before use (do not dilute!).
- Apply the primer on prepared surface to the cleanliness degree Sa 2½ (according to ISO 8501).  
In justified cases, it is allowed to prepare the surface to the degree of cleanliness St3 (mechanically, using steel rotating brushes).
- Apply a thin layer with a brush, brush, sponge, or spray. Do not use naked flames during application - primer and vapors are flammable!

### STORAGE

- Store the product in dry area in original packaging.
- Protect the cartons against mechanical damage.
- The recommended storage temperature: up to 25°C.

### PRODUCT FORM & SIZE AVAILABLE

Can: 1 litre.